

TRESTJERNER Gulvmatt

Product description

Type

Fully matted floor varnish for wood and parquet.

Features and benefits

Waterborne and odorless. Has the appearance of oil and the varnish's durability. Provides no visible varnish film. The product provides a transparent, completely matte, warm and moderate expression - which emphasizes the natural appearance of the wood.

Recommended use

Floors and stairs in solid wood and parquet, as well as furniture. To be used on untreated, varnished, oiled and substrates treated with lye.

Product data

Packaging size	0.75 L and 3 L.
Tinting	Shall not be tinted.
Gloss level	At 60°: 2-5. At 85°: 3-6.
Generic type	Water thinned acrylic / -polyuretan varnish.
Solids by volume	27 ± 2 volume%
Specific gravity	1.04
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/i): 140 g/l. The product contains max 80 g/l VOC.

Application data

Remarks

Contents of tins with different production numbers should be mixed. "New and better" should not be mixed with previous version of the product. Stir well before and during use.

Application equipment / methods

Jordan Gulvlakkpensel Perfect or Jordan Malerull Perfect for jevne flater.
Pour an appropriate amount of varnish on the floor, and spread it evenly and richly in the length of the boards. Apply rich and evenly. Work quickly and efficiently to avoid returning to semi-dry varnish.

Cleaning of painting tools

Water.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)

Recommended:	8 - 10	100 - 125	27 - 34
---------------------	--------	-----------	---------

Thinner

Shall not be thinned.

Conditions during application

The air and surface temperature must be above + 5 °C.

Drying times

Low temperature, high humidity and consumption beyond the recommended amount will prolong the drying time and recoating interval.

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C

Recoat after	4 h
Dry to use / careful use	8 h
Excessive loads / fully cured	2 weeks

Directions for use

Surface preparation

The substrate must be sound, clean, dry and free from grease, detergent, wax etc. All substrates must first be cleaned with **TRESTJERNER Gulvrens**.
Varnished and former factory-laquered surfaces should be roughened with abrasive paper no. 150-180. Use grinding machine to ensure smooth and accurate matting. Vacuum and wipe the surface with a microfiber floor cloth.

Topcoat

TRESTJERNER Gulvmatt.
Apply 3 coats to new and untreated floors.
Apply 2 coats to previously lacquered floors.
Apply 2 coats to previously oiled floors. NB! On previously oiled floors it is important to test first, to make sure the varnish is compatible with the oil.

Maintenance

Avoid washing and carpets on the floor the first 2 weeks after lacquering.

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

Storage

In storage and in transport keep the container frost free and upright.

Disposal of waste

Empty containers and laquer residue must be brought to a local recycling station.



TOMTOGTORT.NO

Environmental labelling

BREEAM® NOR

The product is tested after 3 days (SP) according to the testing requirements set by BREEAM NOR.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

NOBB number

This document covers the following NOBB numbers:

49424692, 49424703

NOBB module number

22531545

Contact information

Scanox AS
P.O.Box 904 Brakerøya
3002 Drammen
Norway
Tel: +47 32 24 43 00

Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.