

## TYRILIN Interiørvoks

### Product description

#### Type

**TYRILIN Interiørvoks** is made of beeswax and oils and is used as finishing treatment on **TYRILIN Interiørbeis** as well as on furniture, tables and benches.

#### Features and benefits

**TYRILIN Interiørvoks** will provide the wood with deeper hue and play of colours, it will counteract drying out and ease the cleaning. The interior wax is almost odorless and dries quickly. The wax emphasizes the natural structure of the wood, with a beautiful luster and shade. The wax will give light wood such as oak, ash, maple, pine and spruce a golden silk matt and resistant surface.

#### Recommended use

Used as finishing treatment on **TYRILIN Interiørbeis**. **TYRILIN Interiørvoks** used for walls and ceilings made from panels and notched timber, as well as other interior such as furniture, doors, etc. Can also be used on untreated walls, ceilings and furniture.

### Product data

<b>Packaging size</b>	1 liter plastic bottle.
<b>Flash point</b>	Closed cup: >62°C (>143.6°F)
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/i): 500 g/l. The product contains max 0 g/l VOC.

### Application data

#### Application equipment / methods

Varnish brush and / or lint-free cloth.

#### Cleaning of painting tools

Cleaning with **TRESTJERNER Gulvrens** and water.

#### Spreading rate and film thickness

#### Spreading rate per coat (m<sup>2</sup>/liter)

**Recommended:** 15 – 25

#### Thinner

Shall not be thinned.

## Drying times

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Dust dry	12 hours
----------	----------

## Directions for use

The surface must be dust free and clean.

Apply **TYRILIN Interiørvoks** with brush or soft, lint-free cloth. If a brush is used, polish the wax with a cloth after a few minutes.

After application, wipe lightly off excess wax as wax will pull unevenly into the wood. If necessary, repeat the wax treatment after the first treatment is dried.

Tables and kitchen counters with high load and use should be re-treated a couple of times a year.

## Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

## Storage

In storage and in transport keep the container frost free and upright. Store at min. +5 °C.

Durability: Unopened approx. 2 years.

## Disposal of waste

Liquid wax must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Must be empty and dry

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

---

## Miscellaneous

### NOBB number

This document covers the following NOBB numbers:

42622663

### Contact information

Scanox AS  
P.O.Box 904 Brakerøya  
3002 Drammen  
Norway  
Tel: +47 32 24 43 00

### Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.