

## SCANOX Finsparkel

### Product description

#### Type

**SCANOX Finsparkel** is based on cellulose derivatives and latex combinations added with fine crushed dolomite.

#### Features and benefits

Easy and smooth to work with, as well as very easy to sand. Provides a very smooth and nice result.

#### Recommended use

**SCANOX Finsparkel** is a filler for plasterboard, smooth ceilings and wall panels. For minor repairs, not furniture. Is used for adding paper strips to gypsum boards, whole-, joint- and spot filling of building boards. Very suitable for spot filling of building boards and old wallpaper.

### Product data

<b>Packaging size</b>	0.4 L tube and 3 L pail.
<b>Colors</b>	Beige.
<b>Solids by volume</b>	45 ± 2 volume%
<b>Filling properties</b>	0–2 mm
<b>pH value</b>	9 (at 10% concentration)

### Application data

#### Application equipment / methods

For manual application.

#### Cleaning of painting tools

Water.

#### Recommended spreading rate

Ca 1.5 l/m<sup>2</sup> per coat by full coverage (filler).

#### Thinner

Should normally not be thinned.

#### Conditions during application

Temperature of air and substrate must be above +10 °C when using the product.

#### Drying times

Low temperature and high humidity prolongs the drying time considerably.

#### The drying time is measured by stated values:

**Relative Humidity (RH)** 50 %

<b>Air temperature</b>	23 °C
<b>Substrate temperature</b>	23 °C
<b>Dust dry</b>	30 min.
<b>Recoatable, minimum</b>	New treatment after 1 day or when the filler is dry.

## Directions for use

Substrate	Treatment
New gypsum boards:	Use <b>SCANOX Finsparkel</b> and <b>JOTUN Sparkelremse papir</b> for joint filling on gypsum boards. A total of 3 layers of filler are added to achieve smooth joints with sanding between each layer on new plasterboard.
Old surfaces with wounds and unevenness in wall and ceiling:	Old surfaces are washed with <b>BUTINOX Interiørvask</b> and sanded. Cut off any loose paper, dents, etc. Remove any protruding unevenness. Spot- or full treatment in the first layer. Sand the surface after drying (1 day). If necessary, 1-2 layers full treatment using <b>SCANOX Finsparkel</b> with sanding between each coat. Make sure the substrate is smooth enough before priming and painting.
Damage to plasterboard:	Major damage to plasterboard is repaired with plaster-based filler.
Damages and roughness of the substrate:	Fill damages and roughness of the substrate with <b>SCANOX Grovsparkel</b> .

## Maintenance

Not applicable. The product is not used alone.

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

## Storage

In storage and in transport keep the container frost free and upright.  
Storage ca 12 months if unopened packaging.

## Disposal of waste

Empty containers and residues of contents are delivered to municipal waste disposal or nearest environmental station.



Must be empty and dry

## Environmental labelling



The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued. Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

## Miscellaneous

### NOBB number

This document covers the following NOBB numbers:

SCANOX Finsparkel: 45433901

SCANOX Finsparkel (tube): 45611557

### NOBB module number

22529218

### Contact information

Scanox AS  
P.O.Box 904 Brakerøya  
3002 Drammen  
Norway  
Tel: +47 32 24 43 00

### Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.