

BUTINOX Interiør Tak

Product description

Type

Completely matt, PVA-based, solvent-free ceiling paint for use indoors.

Features and benefits

Low odor and allergy-friendly paint. Specially designed for ceilings giving a stain free look. The product is easy to apply, dries quickly, has good coverage and does not yellow.

Recommended use

Recommended on ceilings as intermediate and top coat on sandstone, plaster, concrete and building boards surfaces.

Product data

Packaging size	3 L (BASE 2.7 L) and 10 L (BASE 9 L)
Base availability	White
Tinting	Can be tinted to some light colours. Bases must be tinted using Butinox Colour Manager .
Colors	White base may be used untinted as White. Can be tinted to the following colours: SCANOX 5670 Egghvit / JOTUN 1001 Egg White / 0502-Y (NCS) SCANOX 5502 Krem / JOTUN 1453 Cotton / S0502-Y (NCS) SCANOX 5501 Latte / JOTUN 471 Lys Antikk / 0802-G98Y (NCS)
Gloss level	Completely matt 02
Solids by volume	33 ± 2 volume%
Specific gravity	1.4
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. A/a): 30 g/l. The product contains max 1 g/l VOC.

Application data

Remarks

Contents of tins with different production numbers should be mixed to avoid possible colour deviations. Stir well before use.

Application equipment / methods

Roller, brush or spray. Use paint tools from the Jordan Ultimate series to achieve best results result.

Use roller and long handle when painting the ceiling. Then you will cover larger areas at a time. When painting smooth ceilings, work on fields of approx. two meters at a time throughout the length of the ceiling in the direction of light. This is to prevent semi-dry paint from attaching itself on the roller. When painting ceiling boards, fill the profiles with a brush before rolling out the paint field by field.

Guiding data for airless spray

Nozzle tip 0.018 - 0.021" (0.46 - 0.53 mm.)

Spray angle degrees 65–80°
Pressure at nozzle Min. 150–200 kg/cm²

Cleaning of painting tools

Clean with water and brush cleaner. Clean the paint tools in water after use. Use **BUTINOX Penselrens** if the paint is difficult to remove. Use brush cleaner to clean the brushes after use to keep them in good condition for the next paint job.

Spreading rate and film thickness

	Spreading rate per coat (m ² /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
Recommended:	8 – 10	100 – 125	33 – 41

Thinner

Shall not be thinned.

Conditions during application

Temperature of air and substrate must be above +10 °C during painting.

Drying times

Drying times deviate because of changes in temperature, air humidity, air circulation and film thickness.

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Dust dry	1 h
Recoatable, minimum	2 h
Excessive loads / fully cured	4 weeks

Directions for use

Surface preparation

The substrate must be clean, sound and dry. Surfaces to be washed with **BUTINOX Interiørvask**.

Primer

Prime vinyl-coated boards with **BUTINOX Interiør Heftgrunn**.

Topcoat

BUTINOX Interiør Tak: Apply 2 even and rich coats.

Maintenance

The product shall not be washed. Washing will cause stains. Recommend vacuuming with brush, done gently.

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

Storage

In storage and in transport keep the container frost free and upright.

Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Must be empty and dry

Environmental labelling



The product is recognized by Miljømerking Norge, and conforms with the demands of the environmental label Svanen (the swan).

BREEAM® NOR The product is tested after 3 days (RISE) according to the testing requirements set by BREEAM® NOR.

Approvals



The product is recommended by the Swedish Asthma- and Allergy Association (SAAF). Asthma- och allergiförbundets recommendation does not apply during application of the paint. It does not apply until 14 days after application (TVOC <math>< 10 \text{ mcg} / \text{m}^3 / \text{h}</math>). Exercise caution and ventilate during curing time (2 weeks).

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

NOBB number

This document covers the following NOBB numbers:

48271194, 48271436

NOBB module number

41962719

Contact information

Scanox AS
P.O.Box 904 Brakerøya
3002 Drammen
Norway
Tel: +47 32 24 43 00

Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.