

## TRESTJERNER UV Grunning

### Product description

#### Type

1-komponent, vanntynnbar, akrylbasert spesialgrunning.

#### Features and benefits

Produktet gir en fin innfarging/lød, fukter godt og sikrer god vedheft mellom underlag og UV-lakk. Tørker og herder raskt og er enkel å mellomslipe.

#### Recommended use

Use on bare wood and linoleum coating to be refurbished before coating with TRESTJERNER UV Gulvlakk/ TRESTJERNER UV Gulvlakk Pluss. Ubehandlet/nedslipt tre- og parkettgulv. Linoleumsbelegg.

### Product data

<b>Packaging size</b>	5L can.
<b>Solids by volume</b>	38 ± 2 volume%
<b>Specific gravity</b>	1.1
<b>pH value</b>	8
<b>Flash point</b>	105 °C
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/i): 140 g/l. The product contains max 40 g/l VOC.

### Application data

#### Application equipment / methods

Jordan filtrull/mikrofiberrull, lakkspatel eller T-bar applikator.

#### Cleaning of painting tools

Water.

#### Spreading rate and film thickness

Spreading rate per coat (m <sup>2</sup> /liter)	Film thickness per coat (µm)	
	Wet (calculated)	Dry (calculated)
8 - 10	100 - 125	38 - 48

#### Thinner

Shall not be thinned.

### Conditions during application

Temperaturen må være høyere enn +15 °C ved bruk. Temperaturen i gulv, romluft og lakk må holdes mellom 15 °C og 25 °C. Beskytt gulvet mot direkte sollys og skru av all gulvvarme under og etter påføring. Mål overflatefuktigheten i gulvet (for eksempel med en Lignomat Scanner S eller tilsvarende). Relativ fuktighet i rommet bør være mellom 40 % og 60 %.

### Drying times

Low temperature, high humidity and consumption beyond the recommended amount will prolong the drying time and recoating interval.

#### The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Recoatable after	30-60 min
------------------	-----------

## Directions for use

### Surface preparation

The substrate shall be firm, clean and dry. All substrates must first be cleaned with **TRESTJERNER Gulvrens**. Flater av tre/parkett skal være ubehandlet eller nedslipt. Linoleumsgulv skal være strippet/nullstilt ved bruk av egnet polishfjerner og mekanisk belastning/mattsliping.

### Primer

Rist beholderen i 30-60 sekunder og la den hvile i 2-3 minutter med korken av slik at luftboblene i grunningen forsvinner før påføring. Påfør grunningen med lakkrolle, spatel eller T-bar. Unngå å helle grunningen direkte på gulvet. Arbeid raskt og effektivt for å unngå å komme tilbake i halvtørr grunning. Påfør 1 strøk. La tørke og mellomslip om nødvendig (fiberreisning) før lakkering med TRESTJERNER UV Gulvlakk / TRESTJERNER UV Gulvlakk Pluss.

## Storage

Lagres og fraktes frostfritt mellom 5 og 25 °C.

### Shelf life at 73°F (23 °C)

Se best før dato.

## Disposal of waste

Empty containers and laquer residue must be brought to a local recycling station.



## Environmental labelling

**BREEAM**<sup>®</sup> NOR The product is tested after 3 days (SP) according to the testing requirements set by BREEAM NOR.

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued. Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

## Miscellaneous

### NOBB number

This document covers the following NOBB numbers:

48358516

### Contact information

Scanox AS  
P.O.Box 904 Brakerøya  
3002 Drammen  
Norway  
Tel: +47 32 24 43 00

### Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.