

TRESTJERNER Hardvoksolje

Product description

Type

TRESTJERNER Hardvoksolje is a high quality surface treatment for solid wood and parquet flooring based on processed vegetable oils and hard wax.

Features and benefits

The product gives a matte, durable and water-resistant finish that highlights the wood's natural colors and texture.

Recommended use

TRESTJERNER Hardvoksolje can be used for maintenance of previously hardwax-oiled floors. Surface treatment for indoor use on new or sanded wood floors and on sanded parquet flooring, as well as for maintenance of previously hardwax-oiled surfaces. The product can also be used indoors on new or sanded wood such as details, worktops and furniture.

The product meets the requirements for use in contact with foods (EN 1186) when the surface is completely cured.

Please note! The end result is dependent on surface structure and absorbency, number of treatments and application method.

If staining is desired, the floor can be treated first with **TRESTJERNER Gulvolje** (see Technical Data Sheet) and then **TRESTJERNER Hardvoksolje**. Floors, where **TRESTJERNER Gulvolje** have been applied in white, shades of grey and bright colors, can get a more golden look by using **TRESTJERNER Hardvoksolje** as a clear finishing treatment. Dark colors will get a deeper hue when using **TRESTJERNER Hardvoksolje** as a clear finishing treatment.

For maintenance of previously hardwax-oiled surfaces, a test must be carried out to check that the adhesion to **TRESTJERNER Hardvoksolje** is satisfactory. If the hardwax-oil does not adhere satisfactorily to the substrate, the floor should be sanded to bare wood before treatment.

Product data

| | |
|--------------------------------------|---|
| Packaging size | 0.75 L and 3 L |
| Tinting | Shall not be tinted. |
| Colors | Clear |
| Gloss level | Matt 6-10 |
| Solids by volume | 35 ± 2 volume% |
| Specific gravity | 0.93 |
| Flash point | Closed cup: 40°C (104°F) |
| VOC for Ready-for-Use Mixture | EU limit value for the product (cat. A/i): 500 g/l. The product contains max 368 g/l VOC. |

Application data

Remarks

Stir well up from the bottom. Contents of tins with different production numbers should be mixed. **Due to danger of ignition, used cloths must be burned immediately or soaked in water.**

Application equipment / methods

Paint brush (suited for varnish) or roller and paint brush (suited for varnish).

Manual application: Stir well before and during use. Work on one field at a time. Begin to hardwax-oil along the skirtings corresponding to 2-3 floorboards. Apply the hardwax-oil lengthways along the boards in an even and thin coat with a paint brush attached to the extension shaft or a short-haired roll for smooth surfaces. Brush out with a paint brush (suited for varnish) throughout the length of the floorboard. Work like this in fields of 2-3 floorboards at the time until the surface is finished hardwax-oiled. Any unevenness in the substrate due to fibres to be sanded down lightly with sanding paper no. 180.

Mechanical application: Stir well before and during use. Pour a suitable amount of hardwax-oil on the floor and work the oil into the wood with a white or red pad under the polisher. Distribute excess hardwax-oil with the polishing machine and add more as needed. Polish the finished oiled surface with a dry floor cloth underneath the pad. Repeat the polish with dry floor cloths until the surface is dry and has a good finish. When handling large surfaces, work should be divided into smaller areas of 5-6 m².

Cleaning of painting tools

Clean with White Spirit.

Spreading rate and film thickness

| | Spreading rate per coat (m ² /liter) | Film thickness per coat (µm) | |
|---------------------|---|---------------------------------|------------------|
| | | Wet (calculated) | Dry (calculated) |
| Recommended: | 15 - 25 | 40 - 67 | 14 - 23 |

Thinner

The product is ready to use and should not be thinned.

Conditions during application

Ensure good ventilation during application and drying. Temperature of air and substrate must be above +10 °C when using the product.

Drying times

Low temperature, high humidity and consumption beyond the recommended amount will prolong the drying and curing time.

The drying time is measured by stated values:

| | |
|-------------------------------|-------|
| Relative Humidity (RH) | 50 % |
| Air temperature | 23 °C |
| Substrate temperature | 23 °C |

| | |
|---------------------------------|-----------|
| Recoatable, minimum | 6 hours |
| Dry to use / careful use | 12 hours |
| Cured | Ca 7 days |

Exercise caution during the curing period. Avoid carpets on the floor in the first month after treatment.

Directions for use

Surface preparation

All substrates must first be cleaned with **TRESTJERNER Gulvrens**. The surface should be completely clean and dry, and free of grease, soap residues and any wax / polish before varnishing.

| | |
|---|---|
| Previously hardwax-oiled surfaces: | To be sanded with abrasive paper no. 150-180. Be sure to sand between the blocks to avoid cracking flaking. Vacuum and then wipe the surface with a microfiber cloth. Previously hardwax-oiled surfaces with deep scratches and damage should be sanded to bare wood / parquet. |
| Previously laquered and painted surfaces: | To be sanded down to bare wood / parquet. Use grinding machine to ensure smooth and thorough sanding. Finish with 180 grit. Remove dust from sanding. Vacuum and wipe the surface with a microfiber floor cloth. |

Finishing treatment

Apply 2 coats **TRESTJERNER Hardvoksolje** on new and sanded surfaces.

If staining is desired, the floor can be treated first with **TRESTJERNER Gulvolje** (see Technical Data Sheet) and then **TRESTJERNER Hardvoksolje**.

For maintenance of previously hardwax-oiled surfaces, apply 1 coat clear hardwax-oil.

Maintenance

Daily cleaning: Vacuuming / Dry mopping with microfiber cloth.

Regular cleaning (on dirty floors): Cleaning with **TRESTJERNER Oljepleie** and water (ratio 1:20). Use only slightly dampened mop. Avoid water spills on the floor.

Periodic maintenance: **TRESTJERNER Hardvoksolje** can be used for maintenance of previously hardwax-oiled floors. Maintenance must be initiated before the floor is worn down to bare wood. Follow the instructions under Surface preparation and Application equipment/methods.

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

Storage

The product can withstand frost. In storage and in transport keep the container upright.

Disposal of waste

Empty containers and residues of contents are delivered to municipal waste disposal or nearest environmental station.



TOMTOGTORT.NO

Environmental labelling

BREEAM® NOR The product is tested after 3 days (RISE) according to the testing requirements set by BREEAM® NOR.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

NOBB number

This document covers the following NOBB numbers:

49724462, 49724481

NOBB module number

42014345

Contact information

Scanox AS
P.O.Box 904 Brakerøya
3002 Drammen
Norway
Tel: +47 32 24 43 00

Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.