

## TAKSITT Grunning for Takstein

### Product description

#### Type

**TAKSITT Grunning for Takstein** is a water-thin, clear primer specially developed for roof tiles.

#### Features and benefits

It protects against fouling and weathering. The primer provides good penetration and provides good adhesion to **TAKSITT Spesialmaling for Utvendige Tak**.

#### Recommended use

**TAKSITT Grunning for Takstein** is an excellent primer for cement roof tiles. Can also be used on concrete and eternite (not supereternite). If in doubt about treatment, Scanox AS should be contacted.

### Product data

<b>Packaging size</b>	3 and 10 L.
<b>Tinting</b>	Shall not be tinted using <b>BUTINOX Colour Manager</b> .
<b>Gloss level</b>	Matt
<b>Generic type</b>	Acrylic.
<b>Solids by volume</b>	19 ± 2 volume%
<b>Solids by weight</b>	21 ± 2 Theoretical weight %
<b>Specific gravity</b>	1.03 Theoretical
<b>pH value</b>	8.5
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/g): 30 g/l. The product contains max 30 g/l VOC.

### Application data

#### Remarks

Contents of tins with different production numbers should be mixed. Stir well before use.

#### Application equipment / methods

Roller, brush or spray.

When using a roller and brush it is recommended to apply a full coat with the roller first. Then use the brush and apply the primer carefully on all edges and corners. Work in smaller fields at a time to ensure that overlaps are not visible. Take for example 2-3 roofs tiles width and work your way from top to bottom.

#### Guiding data for airless spray

<b>Nozzle tip</b>	0.017–0.023"
<b>Spray angle degrees</b>	40–50°
<b>Pressure at nozzle</b>	Min. 15 MPa (Min. 150 kg/cm <sup>2</sup> )

#### Cleaning of painting tools

Water and **BUTINOX Penselrens**.

## Spreading rate and film thickness

	Spreading rate per coat (m <sup>2</sup> /liter)	Film thickness per coat (µm)	
		Wet (calculated)	Dry (calculated)
<b>Recommended:</b>	5 - 7	143 - 200	27 - 38
<b>Comments:</b>	Dependent on the surface texture.		

## Thinner

Shall not be thinned.

## Conditions during application

Air and surface temperature must be above +10 °C during application. Not to be used in direct sunshine. Do not paint if there is a risk of condensation or rain and wait until the film is dry.

## Drying times

The drying time is measured by stated values:

<b>Relative Humidity (RH)</b>	50 %
<b>Air temperature</b>	23 °C
<b>Substrate temperature</b>	23 °C

<b>Recoatable, minimum</b>	4 h
<b>Must be repainted within</b>	2 days

The product should be overcoated.

## Directions for use

Substrate	Treatment
<b>Cement roof tiles:</b>	Use a pressure washer and rinse thoroughly away all the loose sand particles, algae, fungi and moss. Walk carefully, it is safest to walk where it is either already flushed completely or where the substrate is completely dry. See more information about safety in the brochure and at <a href="http://www.scanox.no">www.scanox.no</a> . The roof tiles should be dry before applying 1-2 coats <b>TAKSITT Grunning for Takstein</b> , depending on the condition of the substrate. When the primer has dried, apply 2 coats <b>TAKSITT Spesialmaling for Utvendige Tak</b> .
<b>Eternit:</b>	Use a pressure washer and rinse thoroughly away all the loose sand particles, algae, fungi and moss. Walk carefully, it is safest to walk where it is either already flushed completely or where the substrate is completely dry. See more information about safety in the brochure and at <a href="http://www.scanox.no">www.scanox.no</a> . The roof tile must be dry before applying 1 coat of <b>TAKSITT Grunning for Takstein</b> , depending on the condition of the substrate. When the primer has dried, apply 2 coats <b>TAKSITT Spesialmaling for Utvendige Tak</b> .

## Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

## Storage

In storage and in transport keep the container frost free and upright.

## Disposal of waste

Liquid paint must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Must be empty and dry

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

## Miscellaneous

### NOBB number

This document covers the following NOBB numbers:

51408745, 51408753

### Contact information

Scanox AS  
P.O.Box 904 Brakerøya  
3002 Drammen  
Norway  
Tel: +47 32 24 43 00

### Disclaimer

# Technical Data Sheet

## TAKSITT Grunning for Takstein



The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.

This technical data sheet supersedes those previously issued.

The Technical Data Sheet (TDS) is recommended to be read in conjunction with the Safety Data Sheet (SDS) for this product. For your nearest local Scanox office, please visit our website at [www.scanox.no](http://www.scanox.no).