

## QUICK Bengalack Grunning Spray

### Product description

#### Type

**QUICK Bengalack Grunning Spray** (Arcanol) is an anti corrosive alkyd primer.

#### Features and benefits

**QUICK Bengalack Grunning Spray** is a weather-resistant primer for metal/anti corrosive alkyd paint. The primer can also be used as topcoat, and will then give it a satin appearance. Particularly well suited in areas where it is difficult to reach by brush.

#### Recommended use

To be used indoors and outdoors as protective primer on iron, steel, zinc and galvanized surfaces like corrugated sheet metal, etc. The primer can also be used on hard plastics. Can be used on surfaces where temperatures will not exceed 90 ° C.

### Product data

|                                      |   |
|--------------------------------------|---|
| <b>Packaging size</b>                | Spray can (net content about 400 ml).   |
| <b>Colors</b>                        | 340 Metal Grey.   |
| <b>Gloss level</b>                   | Silky matt.   |
| <b>Flash point</b>                   | Closed cup: -7°C (19.4°F)   |
| <b>VOC for Ready-for-Use Mixture</b> | EU limit value for the product (cat. B/e): 840 g/l. The product contains max 840 g/l VOC. |

### Application data

#### Remarks

Propellant: Butane/propane.  
The product is classified as extremely flammable.

#### Application equipment / methods

Shake vigorously for 2 min. before use.

Keep the box as vertical as possible during spraying. Spray evenly and thinly at a distance of approx. 30 cm. Keep the can in motion during application. First spray in horizontal direction. After 5 min., spray in vertical direction. Repeat with approx. 5 min. intervals until desired effect.

After use, turn the box upside down and spray until only propellant gas comes out.

#### Conditions during application

Do not paint if there is a risk of condensation or rain and wait until the film is dry.

#### Drying times

The drying time is affected by temperature, air humidity and film thickness.

#### The drying time is measured by stated values:

**Relative Humidity (RH)** 50 %

|                       |       |
|-----------------------|-------|
| Air temperature       | 23 °C |
| Substrate temperature | 23 °C |

|                               |              |
|-------------------------------|--------------|
| Recoatable, minimum           | Ca 5 minutes |
| Dry to use / careful use      | Min. 3 hours |
| Excessive loads / fully cured | 3–4 weeks    |

## Directions for use

### Surface preparation

The substrate must be clean, sound and dry.

| Substrate                          | Treatment   |
|------------------------------------|---|
| New iron and steel:                | Degrease with <b>UNIVERSALTYNNER NR. 1</b> or <b>QUICK Bengalack Avfetting Spray</b> .<br>Wash with <b>BUTINOX Kraftvask</b> . Rinse with water.<br>The substrate must be completely dry before further treatment.  |
| Previously painted iron and steel: | Remove all rust, loose paint, grease and other contaminants. Existing paint should be sanded.<br>Wash with <b>BUTINOX Kraftvask</b> . Rinse with water.<br>The substrate must be completely dry before further treatment.                                 |
| Galvanised steel and aluminium:    | Degrease with <b>UNIVERSALTYNNER NR. 1</b> or <b>QUICK Bengalack Avfetting Spray</b> .<br>Wash with <b>BUTINOX Kraftvask</b> diluted 1:5 with water. RINSE THOROUGHLY with fresh water!<br>The substrate must be completely dry before further treatment. |
| Hard plastics and wood:            | The substrate shall be free from grease and other contaminants.<br>Wash with <b>BUTINOX Husvask/Kraftvask</b> . Rinse with water.<br>The substrate must be completely dry before further treatment.   |

### Pretreatment

2 coats **QUICK Bengalack Grunning Spray**.

### Topcoat

**QUICK Bengalack Grunning Spray** can be used as a topcoat, but an extra coat should then be applied (total of 3 coats).

## Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

## Storage

In storage and in transport keep the container upright. Can be stored in freezing temperatures.

## Disposal of waste

Empty containers and paint residues must be delivered at community waste disposal or the nearest recycling center.



## Environmental labelling

**BREEAM® NOR** The product meets the requirements of the BREEAM-NOR for the VOC and the A20 list.

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

## Miscellaneous

### NOBB number

This document covers the following NOBB numbers:

55808423

### NOBB module number

42169204

### Contact information

Scanox AS  
P.O.Box 904 Brakerøya  
3002 Drammen  
Norway

Tel: +47 32 24 43 00  
Fax: +47 32 84 13 85  
SDSscanox@scanox.no

### Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.