

## TYRILIN Panelhvit

### Product description

#### Type

TYRILIN Panelhvit is a waterborne surface treatment that provides a white toned, bright natural look.

#### Features and benefits

The product contains natural oils, waxes, UV filters and antioxidants that effectively protect wood against yellowing. Very low odor. Easy to apply. The product is ready to use and can be applied in one or two coats. Depending on the desired appearance.

#### Recommended use

TYRILIN Panelhvit is used indoors on previously panel lacquered, oiled, stained and untreated wood panels on ceilings and walls of pine and spruce - without staining. NB: Not suitable for high load surfaces (floors, etc.).

### Product data

<b>Packaging size</b>	3 liter.
<b>Specific gravity</b>	1.2
<b>pH value</b>	9
<b>Flash point</b>	Closed cup: 62°C (143.6°F)
<b>VOC for Ready-for-Use Mixture</b>	EU limit value for the product (cat. A/d): 130 g/l. The product contains max 42 g/l VOC.

### Application data

#### Remarks

Stir well before use. Contents of tins with different production numbers should be mixed.

#### Application equipment / methods

Paint brush (suited for varnish), brush (suited for levelling out the paint/stain/varnish).

Apply the product along the full length of 1 – 2 boards at a time. Brush out in the full length of the board to avoid mismatch in the overlap section.

#### Cleaning of painting tools

Cleaning with some soap and water.

#### Spreading rate and film thickness

#### Spreading rate per coat (m<sup>2</sup>/liter)

**Recommended:** 15 – 30

#### Thinner

Water.

### Conditions during application

Air and surface temperature must be above +10 °C during application. Best results are achieved at room temperature of about 15 °C due to fast drying.

### Drying times

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C
Substrate temperature	23 °C

Recoatable, minimum	From 2 hours to 1 day depending on the substrate and temperature.
Dry to use / careful use	Ca 2 hours.
Excessive loads / fully cured	1–3 weeks.

## Directions for use

### Surface preparation

The substrate must be clean, sound and dry. Always clean with **TYRILIN Panelrens** first.

### Topcoat

1–2 coats TYRILIN Panelhvit. If you want a whiter appearance, apply a new coat after the first coat is dry.

## Maintenance

Please refer to the FDV datasheet for information regarding maintenance and repair of the painted surface.

## Storage

In storage and in transport keep the container frost free and upright.

### Shelf life at 73°F (23 °C)

Durability: 2 years in unopened container.

## Disposal of waste

The product must not be emptied into drains or watercourses. It must be delivered to an approved local environmental protection station.



Must be empty and dry

## Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

**First-aid measures**, refer to section 4.

**Handling and storage**, refer to section 7.

**Transport information**, refer to section 14.

**Regulatory information**, refer to section 15.

## Miscellaneous

### NOBB number

This document covers the following NOBB numbers:

41523275

### Contact information

Scanox AS  
P.O.Box 904 Brakerøya  
3002 Drammen  
Norway

Tel: +47 32 24 43 00  
Fax: +47 32 84 13 85  
SDSscanox@scanox.no

### Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.